

H01 - H-NBR green

Highly saturated nitrile butadiene rubber

Mechanical, Physical and Thermal Properties

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				green		green
hardness	23°C/3 sek.	ISO 868	Shore A	85 ± 5	Shore A	85 ± 5
hardness	23°C/15 sek.	ISO 868	Shore A	81 ± 5	Shore A	81 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 10	psi	≥ 1450
tensile strength	23°C	DIN 53 504	MPa	≥ 17	psi	≥ 2465
elongation at break	23°C	DIN 53 504	%	≥ 165	%	≥ 165
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 15	lbf/inch	≥ 85
spec. gravity	23°C	ISO 1183	kg/m ³	1320	g/cm ³	1,32
rebound elasticity	23°C	DIN 53 512	%	29	%	29
abrasion	23°C	DIN 53 516	mm ³	135	mm ³	135
compression set	*	ISO 815	%	≤ 12	%	≤ 12
compression set	**	ISO 815	%	≤ 14	%	≤ 14
compression set	***	ISO 815	%	≤ 22	%	≤ 22
minimum service temperature			°C	-20	°F	-4
maximum service temperature			°C	150	°F	302
temp. max water/steam			°C	120	°F	248
temp. max hot air			°C	180	°F	356

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on butadiene and acrylonitrile

Resistant to: oil, petrol, crude oil

Not resistant to: conc. Acides, conc.lyes and polar solvents