

F06 - PTFE Azzurro

Physical - Mechanical

PROPERTIES	UNIT	METHOD	DATA - MOULDED
Density	g/cm³	ASTM D792	2,15 - 2,25
Hardness - Shore D	/	ASTM D2240	≥ 62
Tensile Strength - CD	N/mm²	ISO12086 - ISO 527	≥ 14
Elongation at break - CD	%	ISO 12086 - ISO 527	≥ 230
Deformation under load at room temperature after 24 hours at 13,7 N/mm ² - CD	%	ASTM D621	≤ 10
Permanent deformation as above after 24 hours of rest at room temperature - CD	%	ASTM D621	≤ 6

Tribological

PROPERTIES	UNIT	METHOD	DATA - MOULDED
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,15 - 0,25

Thermal

PROPERTIES	UNIT	METHOD	DATA - MOULDED
Service Temperature (min - max)	°C	/	- 200 / + 260
Thermal expansion coefficient (linear) 25 - 100°C	10 ⁻⁵ (mm/mm)/ °C	Simile a ASTM D696	9 - 11

Electrical

PROPERTIES	UNIT	METHOD	DATA - MOULDED
Volume Resistivity	$\Omega \cdot cm$	ASTM D257	≥ 10 ¹⁵
Surface Resistivity	Ω	ASTM D257	≥ 10 ¹⁵

CD=Cross Direction

The data we are herewith providing are all based on laboratory testing and are proposed to technical designers as possible and useful advice. Deviations from the values hereabove indicated may occur, but they do not constitute themselves either detriment of quality or reason for rejection.

Revisione 07.25